

SILICÓN TRANSPARENTE USO GENERAL CARTUCHO 300ml WESTON[®] WM-0925

CONFIDENCIAL

NO: Q/JLR202307577

DELIVERY INSPECTION REPORT

Product Name: Acetic Silicone
 Product Brand: WM-0925
 Product Color: 010 Translucent
 PI NO: PG231889
 PO NO: 6697

Sample NO: SSX20230620-1766-12962
 Quantity: 3 Pieces
 Arrival Date: 2023-06-20
 Contract NO: L017G231205
 Batch NO: PROD:16/06/2023 BATCH
NO:L0171205

Temperatur: 23°C

Relative humidity: 50%

No	Items	C*a/T*b/S*c/O*d	Unit	Requirement	Value	Decision	Test Std	Eqv. Std
1	Curing Depth	7d///	mm	≥5.0	6	Pass	GB/T 32369	
2	Density	///	g/cm3	0.96±0.10	0.97	Pass	GB/T 13477.2	
3	Hardness, Shore A	7d///	/	20~30	23	Pass	GB/T 531.1	ISO 48-4
4	Curing Depth	24h///	mm	≥2.0	3	Pass	GB/T 32369	
5	Appearance	///	/	Fine, uniform paste	OK	Pass	Q/JL-00-T001	
6	Sagging	///	mm	≤1	0	Pass	GB/T 13477.6	ISO 7390
7	Elongation at break	7d///	%	≥600	929	Pass	GB/T 528	ISO 37
8	Tack free	///Finger	min	≤15	6	Pass	GB/T 13477.5	ASTM D2377:2000
9	Tensile Strength	7d///	MPa	≥0.8	1.59	Pass	GB/T 528	ISO 37

Notes: **The test result is only limited to the submitted samples.**
 *a, Conditioning, specimen is conditioned under (23±2) °C, (50±5)% relative humidity if not specified;
 *b, Testing Condition, specimen is tested at (23±2) °C, (50±5)% relative humidity if not specified;
 *c, Substrate;
 *d, Others need to be specified.

Compiled By:		Check By:	
Date:	2023.07.08	Date:	2023.07.10

The Test Center has been certified according to ISO/IEC 17025:2017.

The management system has been certified according to ISO 9001:2015, ISO 14001:2015, ISO 45001:2018.